

Eagle Window & Door

Ascent® Sliding French Door Sidelite

3068 Tested Size at DP 40

Series 05 Ascent Clad French Sliding Door Sidelite

Glass Type	Divided Light Options	U-VAL	SHGC	VLT	CR	Energy Star Zone
High-Performance™ Low-E4™ 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.34	0.24	0.41	57	2
	7/8" CDL	0.34	0.22	0.35	57	2
	1-1/8" & 1-1/2" CDL	0.34	0.19	0.31	57	2
	5/8" Between-glass Grilles	0.36	0.22	0.35	57	8
	1" Between-glass Grilles	0.36	0.22	0.35	57	8
	5/8" MDL	0.36	0.22	0.35	57	8
	7/8" MDL	0.36	0.22	0.35	57	8
	1-1/2" MDL	0.38	0.19	0.31	57	8
High-Performance™ Low-E4™ High Altitude 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.37	0.25	0.41	54	8
	7/8" CDL	0.37	0.22	0.35	54	8
	1-1/8" & 1-1/2" CDL	0.37	0.19	0.31	54	8
	5/8" Between-glass Grilles	0.38	0.22	0.35	54	8
	1" Between-glass Grilles	0.38	0.22	0.35	54	8
	5/8" MDL	0.38	0.22	0.35	54	8
	7/8" MDL	0.38	0.22	0.35	54	8
	1-1/2" MDL	0.39	0.19	0.31	54	8
High-Performance™ Low-E4™ Gray Tint 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.34	0.22	0.28	57	2
	7/8" CDL	0.34	0.20	0.24	57	2
	1-1/8" & 1-1/2" CDL	0.34	0.18	0.21	57	2
	5/8" Between-glass Grilles	0.36	0.20	0.24	57	8
	1" Between-glass Grilles	0.36	0.20	0.24	57	8
	5/8" MDL	0.36	0.20	0.24	57	8
	7/8" MDL	0.36	0.20	0.24	57	8
	1-1/2" MDL	0.38	0.18	0.21	57	8
High-Performance™ Low-E4™ Gray Tint High Altitude 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.37	0.23	0.28	54	8
	7/8" CDL	0.37	0.20	0.24	54	8
	1-1/8" & 1-1/2" CDL	0.37	0.18	0.21	54	8
	5/8" Between-glass Grilles	0.38	0.20	0.24	54	8
	1" Between-glass Grilles	0.38	0.20	0.24	54	8
	5/8" MDL	0.38	0.20	0.24	54	8
	7/8" MDL	0.38	0.20	0.24	54	8
	1-1/2" MDL	0.39	0.18	0.21	54	8
High-Performance™ Low-E4™ Bronze Tint 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.34	0.23	0.30	57	2
	7/8" CDL	0.34	0.21	0.26	57	2
	1-1/8" & 1-1/2" CDL	0.34	0.18	0.23	57	2
	5/8" Between-glass Grilles	0.36	0.21	0.26	57	8
	1" Between-glass Grilles	0.36	0.21	0.26	57	8
	5/8" MDL	0.36	0.21	0.26	57	8
	7/8" MDL	0.36	0.21	0.26	57	8
	1-1/2" MDL	0.38	0.18	0.23	57	8
	1-1/8" MDL	0.36	0.18	0.23	57	8

Eagle Window & Door

Ascent® Sliding French Door Sidelite

3068 Tested Size at DP 40

Series 05 Ascent Clad French Sliding Door Sidelite

Glass Type	Divided Light Options	U-VAL	SHGC	VLT	CR	Energy Star Zone
High-Performance™ Low-E4™ Bronze Tint High Altitude 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.37	0.23	0.30	54	8
	7/8" CDL	0.37	0.21	0.26	54	8
	1-1/8" & 1-1/2" CDL	0.37	0.18	0.23	54	8
	5/8" Between-glass Grilles	0.38	0.21	0.26	54	8
	1" Between-glass Grilles	0.38	0.21	0.26	54	8
	5/8" MDL	0.38	0.21	0.26	54	8
	7/8" MDL	0.38	0.21	0.26	54	8
	1-1/2" MDL	0.39	0.18	0.23	54	8
Low-E 240 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.39	0.15	0.23	57	8
	7/8" CDL	0.39	0.14	0.20	57	8
	1-1/8" & 1-1/2" CDL	0.39	0.12	0.17	57	8
	5/8" Between-glass Grilles	0.40	0.14	0.20	57	8
	1" Between-glass Grilles	0.40	0.14	0.20	57	8
	5/8" MDL	0.40	0.14	0.20	57	8
	7/8" MDL	0.40	0.14	0.20	57	8
	1-1/2" MDL	0.41	0.12	0.17	57	5
Low-E 240 High Altitude 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.41	0.16	0.23	54	5
	7/8" CDL	0.41	0.14	0.20	54	5
	1-1/8" & 1-1/2" CDL	0.41	0.13	0.17	54	5
	5/8" Between-glass Grilles	0.41	0.14	0.20	54	5
	1" Between-glass Grilles	0.41	0.14	0.20	54	5
	5/8" MDL	0.41	0.14	0.20	54	5
	7/8" MDL	0.41	0.14	0.20	54	5
	1-1/2" MDL	0.43	0.13	0.17	54	5
Low-E 366 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.38	0.17	0.37	57	8
	7/8" CDL	0.38	0.15	0.32	57	8
	1-1/8" & 1-1/2" CDL	0.38	0.13	0.28	57	8
	5/8" Between-glass Grilles	0.39	0.15	0.32	57	8
	1" Between-glass Grilles	0.39	0.15	0.32	57	8
	5/8" MDL	0.39	0.15	0.32	57	8
	7/8" MDL	0.39	0.15	0.32	57	8
	1-1/2" MDL	0.40	0.13	0.28	57	8
Low-E 366 High Altitude 3.1mm / 13mm / 3.1mm	No Between-glass Grilles or MDL	0.40	0.17	0.37	55	8
	7/8" CDL	0.40	0.15	0.32	55	8
	1-1/8" & 1-1/2" CDL	0.40	0.13	0.28	55	8
	5/8" Between-glass Grilles	0.41	0.15	0.32	55	5
	1" Between-glass Grilles	0.41	0.15	0.32	55	5
	5/8" MDL	0.41	0.15	0.32	55	5
	7/8" MDL	0.41	0.15	0.32	55	5
	1-1/2" MDL	0.42	0.13	0.28	55	5
1-1/8" MDL	0.41	0.13	0.28	55	5	

U-Factor - Rate of Heat Loss = 1/R
 SHGC - Solar Heat Gain Coefficient
 VLT- Visible Light Transmittance
 CR - Condensation Resistance